



McGuinness Works, Mount Osborne Industrial Park,
Oakwell View, Barnsley, South Yorkshire
S71 1HH, United Kingdom
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

Specification Sheet: C4324

Product: *Compressed Non Asbestos Jointing*

Trade Name: *C4324*

Description: *Medium quality compressed jointing based on aramid and glass fibres with NBR binder.*

Service: *General purpose commercial material suitable for oils, fuels, low pressure steam, water and excellent resistance to gas leakage.*

Recommended Max Temperature: *300°C*

Recommended Max Pressure: *5MPa Liquids*

Recommended Max Pressure: *2.5MPa Steam*

Max Steam Temperature: *180°C*

Physical Properties: *Specific Gravity 1.85*
Compressibility ASTM F36A 10%
Stress Relaxation DIN 52913 20MPa
Stress Relaxation BS 7531 23Pa
Gas Leakage DIN 3535/6 <0.1ml/min
Thickness Increase
ASTM Oil No 3 5 hrs at 150°C 0-10%
ASTM F146 Fuel B 5 hrs at 20°C 0-10%

Specification Compliance: *BS 7531 Grade Y*
DIN-DVGW 95.01e 052
SVGW 95-043-7
KTW C 027/95/ST
WRAS Approval No 0202501