



McGuinness Works, Mount Osborne Industrial Park,
Oakwell View, Barnsley, South Yorkshire
S71 1HH, United Kingdom
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

Specification Sheet: **C4400**

Product: *Compressed Non Asbestos Jointing*

Trade Name: *C4400*

Description: *Premium Quality compressed synthetic fibre jointing composed of aramid fibres with NBR binder. Meets the requirements of BS 7531 Grade Y.*

Service: *General purpose material suitable for use with air, water, steam, oils, fuels and gases. Particularly suitable for use on internal combustion engines, compressors and hydraulic applications.*

Recommended Max Temperature: *400°C*

Recommended Max Pressure: *100 bar*

Max Steam Temperature: *200°C*

Physical Properties:

Specific Gravity 1.6

ASTM Compressibility 8%

ASTM Recovery Min 50%

Thickness Increase

ASTM Oil 3 5 hrs at 150°C 0 - 5%

ASTM Fuel A 5 hrs at 20°C 0 - 5%

ASTM Fuel B 5 hrs at 20°C 0 - 5%

The above information is reproduced by courtesy of R. Klinger Limited.