



McGuinness Works, Mount Osborne Industrial Park,
Oakwell View, Barnsley, South Yorkshire
S71 1HH, United Kingdom
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

Specification Sheet: **SPG4002**

Product: Fluorocarbon Rubber

Trade Name: *Viton*

Description: *Viton is a fluorinated hydrocarbon polymer possessing the elasticity of rubber.*

Service: *Suitable for use at high temperatures and in hostile environments where normal synthetic rubbers are not suited. Used widely in the chemical and oil industries.*

Recommended Min Temp -30°C
Recommended Max Temp +250°C

Physical Properties:

Specific Gravity 2.1
Tensile Strength 4.9 MPa
Elongation at Break 190%
Compression Set After 22 hours at 177°C 42%

Figures shown in this data sheet are typical values. The above information is supplied in good faith but no liability is accepted by SPG Ltd. The data sheet does not act as a warranty and the end user should satisfy themselves of its suitability of the product for its intended use.