



McGuinness Works, Mount Osborne Industrial Park,  
Oakwell View, Barnsley, South Yorkshire  
S71 1HH, United Kingdom  
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558  
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

## Specification Sheet: **SPG4003**

**Product:** Silicone

**Hardness:** 50° ±5 Shore A

**Specific Application:**

None, maximum temperature ca 200°C, ozon, UV, heat ageing and water resistant.

**Approval:** None

**Properties:**

Hardness DIN 53505	50° ±5 Shore A
Tensile Strength DIN53504 S2	>60N/mm <sup>2</sup>
Elongation DIN53504 S2	>350%
Specific Gravity DIN53517A	1.14±0.02 g/cm <sup>3</sup>

**Compression Set:** 22 hours in air at 175°C <30%

*Figures shown in this data sheet are typical values. The above information is supplied in good faith but no liability is accepted by SPG Ltd. The data sheet does not act as a warranty and the end user should satisfy themselves of its suitability of the product for its intended use.*