



McGuinness Works, Mount Osborne Industrial Park,
Oakwell View, Barnsley, South Yorkshire
S71 1HH, United Kingdom
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

Specification Sheet: SPG4017

Product : Commercial Grade Neoprene Rubber

Trade Name : N 9580

Description: *A rubber sheeting with CR-SBR Elastomer.*

Service: *For applications involving only low requirements, weather resistant.*

Operations Temperatures:

Short Term (10 hr): +90 °C
Continuous (1000 hr): -10 to + 70 °C

Physical Properties:

Hardness 60° +/- 7 Shore A
Density 1.36 +/- 0.05 gm/cm³
Tensile Strength 3.0 N/mm²
Elongation at Break 250 %

Accelerated ageing in heated air @ 70°C for 70 hours

Change in Hardness: + 10°
Change in Tensile: +/- 25
Change in Elongation at break: -50

Figures shown in this data sheet are typical values. The above information is supplied in good faith but no liability is accepted by SPG Ltd. The data sheet does not act as a warranty and the end user should satisfy themselves of its suitability of the product for its intended use.