



McGuinness Works, Mount Osborne Industrial Park,
Oakwell View, Barnsley, South Yorkshire
S71 1HH, United Kingdom
Tel: +44 (0)1226 329200 Fax: +44 (0)1226 204558
email: sales@spg-gaskets.co.uk www.spg-gaskets.co.uk

Specification Sheet: SPG4362

Base Polymer	EPDM Rubber
Colour	Black
Hardness	70° +/- 5° Shore A
Specific Gravity	1.18g/cm³
Tensile Strength	12 Mpa
Elongation at break	350%
Compression Set (22h @ 70°C)	20%
Heat Ageing(in Air Ventiated Oven) Standard ASTM D573(70 C 70 h)	Hard Inc ShA5 Tensile.Inc % -15 Elong. Inc % -40 + 5 Shore A +8% -15% -40°C - + 120°C
Change in Hardness	
Change in Tensile	
Change in Elongation	
Temperature Range	
Chemical Resistance	
Ozone	Excellent
Diluted Acids and Oils	Excellent

**Conforms to BS6920 WRC approved, black EPDM rubber for use in contact with potable water.
WRAS listing number 0301528**

Figures shown in this data sheet are typical values. The above information is supplied in good faith but no liability is accepted by SPG Ltd. The data sheet does not act as a warranty and the end user should satisfy themselves of its suitability of the product for its intended use.